

Europäisches Patentamt  
European Patent Office  
Office européen des brevets



(11) **EP 1 066 810 A2**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
10.01.2001 Bulletin 2001/02

(51) Int. Cl.<sup>7</sup>: **A61F 13/15**

(21) Application number: **00114416.1**

(22) Date of filing: **05.07.2000**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE**  
Designated Extension States:  
**AL LT LV MK RO SI**

(30) Priority: **07.07.1999 US 348956**

(71) Applicant: **McNeil-PPC, Inc.**  
**Skillman, NJ 08558-9418 (US)**

(72) Inventors:  
• **Bissah, Kofi Ayensu**  
**Somerset, NJ 08873 (US)**  
• **Corley, Michelle Renee**  
**West Windsor, NJ 08550 (US)**  
• **Haarer Jutta S.**  
**Lawrenceville NJ 08648 (US)**

(74) Representative:  
**Groening, Hans Wilhelm, Dipl.-Ing.**  
**BOEHMERT & BOEHMERT**  
**Franz-Joseph-Strasse 38**  
**80801 München (DE)**

(54) **Bunching resistant absorbent article**

(57) An absorbent article, such as a pantliner, is provided having excellent resistance to bunching. The absorbent article exhibits a Bunching Resistance in the range of about 205g to 450 g and may be formed with an absorbent core comprising at least two absorbent layers having different Gurley Stiffnesses.

**EP 1 066 810 A2**

**Description**

[0001] The present invention relates to an absorbent article having excellent resistance to bunching. The absorbent article exhibits a Bunching Resistance in the range of about 205 g to about 450 g and may be formed with an absorbent core comprising at least two absorbent layers having different Gurley Stiffnesses.

**Background of the Invention**

[0002] An absorbent article such as a sanitary napkin, pantiliner, diaper, incontinence pad, or interlabial article typically comprises a liquid permeable cover on its body facing side, a barrier on its garment facing side, and an absorbent core in between. A common problem with absorbent articles is bunching and deformation of the article due to movement of the person wearing it. Bunching and deformation in turn impair the ability of the article to absorb exudates from the body.

[0003] Several suggestions for solving the problem of bunching have been made. For example, U.S. Patent No. 4,886,513 to Mason, Jr. et al. discloses a pad comprising a flexibly stiff reinforcing member to maintain the pad's shape. The reinforcing member may be for example a strip of polyethylene extending around the periphery of the pad.

[0004] U.S. Patent Nos. 5,609,588 to DiPalma et al. and 5,803,920 to Gilman et al. relate to the use of a resilient layer of non-absorbent foam in a sanitary napkin. The resilient layer is said to resist bunching during use of the napkin, so that the napkin has reduced twisting and bunching.

[0005] U.S. Patent No. 5,387,208 to Ashton et al. discloses an absorbent article with an absorbent core having improved integrity by virtue of the presence of a primary core integrity layer. The primary core integrity layer is made of a liquid impervious mesh of thermoplastic material, preferably a hot melt adhesive.

[0006] U.S. Patent No. 4,973,325 to Sherrod et al. relates to an absorbent article having a transfer member positioned between two side-by-side absorbents. The transfer member is said to allow the absorbent article to flex in the middle and conform to the body of the wearer, thereby reducing bunching.

[0007] U.S. Patent No. 5,575,786 to Osborn recites in claim 1 a sanitary napkin comprising absorbent portions aligned along the longitudinal centerline of the napkin and peripheral portions aligned adjacent to the absorbent portions. The peripheral portions have a different stiffness than the absorbent portions, and the difference in stiffness is claimed to substantially prevent bunching of the napkin when the napkin is subjected to lateral stresses.

[0008] Despite these attempts at maintaining the physical integrity of absorbent articles, an absorbent article having even better anti-bunching properties is needed. Applicants have identified a class of such absorbent articles. Specifically, the present invention provides an absorbent article, such as a sanitary napkin, pantiliner, diaper, incontinence pad, or an interlabial article, in particular a thin absorbent article, comprising in sequence a liquid permeable cover, an absorbent core, and a barrier, having a caliper of less than 0.2 inches, a length of less than about 8 inches, a width of less than about 4 inches, and a Bunching Resistance of at least about 205 g. Preferably, the absorbent article comprises an absorbent core comprising at least two absorbent layers having different Gurley Stiffnesses.

**Summary of the Invention**

[0009] The present invention provides an absorbent article comprising in sequence a liquid permeable cover, an absorbent core, and a barrier, wherein the absorbent article has a caliper of less than about 0.2 inches, a length of less than about 8 inches, a width of less than about 4 inches, and exhibits a Bunching Resistance of about 205 g to about 450 g.

[0010] The present invention further provides an absorbent article comprising in sequence a liquid permeable cover, an absorbent core comprising at least two absorbent layers having different Gurley Stiffnesses, and a barrier.

**Brief Description of the Drawings**

[0011]

Figure 1 is a perspective view of a pantiliner according to the invention.

Figure 2 depicts the apparatus used for the Curved Longitudinal Bending Test.

**Detailed Description of the Invention**

[0012] The absorbent article may for example be a sanitary napkin, a pantiliner, a diaper, incontinence pad, interlabial article, or other similar product for absorbing exudates from the body, such as menses, urine, and feces. Prefer-

ably, the absorbent article is a sanitary napkin or a pantiliner. Such sanitary napkin or pantiliner may have an approximately rectangular, oval, dogbone, or peanut shape. The absorbent article is thin, i.e., having a caliper of less than about 5 mm. Preferably, the caliper of the absorbent article is less than about 3 mm, more preferably less than about 2.5 mm. The absorbent article has a length of less than about 8 inches, preferably 7 inches, and a width of less than about 4 inches, preferably less than about 3 inches.

[0013] Figure 1 depicts a pantiliner according to the invention, and is used for purposes of illustration in the following description of the invention. The pantiliner shown in Figure 1 comprises in sequence from its body-facing side 1 to its garment-facing side 2 a liquid permeable cover 3, an absorbent core 4, and a barrier 5. The liquid permeable cover 3 of the absorbent article may be formed from any fluid pervious material that is comfortable against the skin and that permits fluid to penetrate to the absorbent core, which retains the fluid. A variety of materials are known for this purpose, and any of these may be used. The cover should retain little or no fluid in its structure to provide a relatively dry surface next to the skin. The cover may be a fibrous non-woven fabric made of fibers or filaments of polymers such as polyethylene, polypropylene, polyester, or cellulose. Alternatively, the cover may be formed from an apertured polymeric film. The thickness of the cover may vary from approximately 0.001 to 0.062 inch, depending on the material chosen. Generally, the liquid permeable cover 3 is a single sheet of material having a width sufficient to cover the body-facing side 1 of the article.

[0014] The absorbent article further comprises a barrier 5 on its garment facing side 2. The barrier is typically liquid impermeable and may comprise any thin, flexible, material such as a polymeric film, for example, polyethylene, polypropylene, or cellophane. Alternatively, the barrier may be a normally fluid permeable material that has been treated to be impermeable, such as impregnated fluid repellent paper or non-woven fabric material, or a flexible foam, such as polyurethane or cross-linked polyethylene. If higher Bunching Resistance is desired, a foam, particularly a closed cell foam, may be used as the barrier. The barrier may be a single or multilayer structure, and may also be "breathable," that is liquid impermeable and vapor permeable. The thickness of the barrier when formed from a polymeric film typically is about 0.0005 to 0.002 inch. A variety of materials are known in the art for use as barriers, and any of these may be used.

[0015] Generally, the barrier 5 has a width sufficient to cover the garment-facing side 2 of the absorbent article. The barrier may extend around the sides of the absorbent core in a C-shaped configuration with the portions of the barrier that are adjacent its longitudinal edges extending upwardly from the garment facing side toward the body facing side of the article.

[0016] The absorbent core 4 comprises at least one absorbent layer 6. In a preferred embodiment of the invention, the absorbent core comprises at least two absorbent layers having different Gurley Stiffnesses. Gurley Stiffness is measured by TAPPI T543 om-94.

[0017] For example, the absorbent core may comprise two absorbent layers, one having a high Gurley Stiffness, i.e., greater than about 100, preferably greater than about 120, more preferably greater than about 150, milligrams, and one having a low Gurley Stiffness, i.e., less than about 50, preferably less than about 40, more preferably less than about 35, milligrams. When two absorbent layers are employed, the first absorbent layer proximal the liquid permeable cover has a low Gurley Stiffness, i.e., less than about 50 milligrams, and the second absorbent layer proximal the barrier has a high Gurley Stiffness, i.e., greater than about 100 milligrams.

[0018] Alternatively, the absorbent core may comprise three absorbent layers with alternating Gurley Stiffnesses: high/low/high or low/high/low. Similarly, the absorbent core may comprise four or more absorbent layers with alternating high and low Gurley Stiffnesses, as desired.

[0019] In another embodiment, the absorbent core comprises a single absorbent layer having zones with different Gurley Stiffnesses. Such zones may result in Gurley Stiffness variations along the length, width, or thickness, or combinations of these, of the absorbent layer.

[0020] Construction of an absorbent core comprising absorbent layers of differing Gurley Stiffnesses advantageously provides the absorbent article with stiffness and flexibility simultaneously. The high Gurley Stiffness layer provides rigidity and stability, while the low Gurley Stiffness layer provides flexibility and suppleness. The total effect of this combined structure results in an absorbent article having superior anti-bunching properties as well as flexibility.

[0021] One particularly useful absorbent core comprises two absorbent layers of thermobond airlaid fibrous web with one or more superabsorbent polymers in between. The first absorbent layer proximal the body facing side of the article comprises about 50 to 65% pulp, the remainder being a combination of polyethylene/polypropylene bicomponent fibers and polyethylene/polyester bicomponent fibers, and has a Gurley Stiffness in the range of about 20 to about 50, preferably about 25 to about 35, milligrams. The second absorbent layer proximal the garment facing side of the article comprises less than about 50 % pulp, the remainder being a combination of polyethylene/polypropylene bicomponent fibers and polyethylene/polyester bicomponent fibers, and has a Gurley Stiffness of about 100 to about 200, preferably about 135 to about 175, milligrams.

[0022] The absorbent article may be applied to the crotch of underpants by placing the garment facing side of the absorbent article against the inside surface of the crotch of the underpants. Strips of pressure sensitive adhesive 7 may

be applied to the garment facing side 2 of the absorbent article to help maintain it in place. As used herein, the term "pressure-sensitive adhesive" refers to any releasable adhesive or releasable tenacious means. Suitable pressure sensitive adhesives include for example water-based adhesives such as acrylate adhesives. Alternatively, the adhesive may comprise rapid setting thermoplastic "hot melt" rubber adhesives or two-sided adhesive tape.

**[0023]** A paper release strip 8 that has been coated on one side, may be applied to protect the strips of adhesive 7 prior to use. The coating, for example silicone, reduces adherence of the coated side of the release strip to the adhesive. The release strip can be formed from any suitable sheet-like material which, when coated, adheres with sufficient tenacity to the adhesive to remain in place prior to use but can be readily removed when the absorbent article is to be used.

**[0024]** The absorbent article may comprise other known materials and layers, such as transfer layers, foam layers, odor control agents, construction adhesives, all of which are known in the art. The absorbent article can optionally be embossed with decorative designs using conventional techniques.

**[0025]** The absorbent core may optionally contain superabsorbent polymers, either in one of more absorbent layers, or preferably in between the absorbent layers. Superabsorbent polymers are used to increase the liquid management properties of absorbent articles, such as capacity and retention of fluids. The amount of superabsorbent polymer contained by the absorbent article may range from about 0.1 to about 5 grams, preferably from about 0.2 to about 2.5 grams, more preferably from about 0.3 to about 1 grams.

**[0026]** The absorbent article has a Bunching Resistance of about 205 to about 450 g, preferably about 250 to about 360 g. Bunching Resistance is measured by the Curved Longitudinal Bending Test, which is carried out on an anatomically shaped apparatus as shown in Figure 2. The apparatus comprises two smooth, convex, stainless steel plates 50 placed at a 40 degree angle from one another to form a v-shaped trough 51. The widest distance (at the top) between the plates 52 is 73 mm and the narrowest distance (at the bottom) 53 is 18 mm. A vertically movable, curved pad holder 54 is supported by a shaft 55 and centered between the plates 50. The shaft 55 is connected to a tensionmeter 56. The holder 54 is placed perpendicular to the horizontal axis of the two plates 50. The tensionmeter 56 measures the compression force needed to deform a sample lengthwise in the narrow gap 53 of 18 mm. The tensionmeter is initially set at 50kg. The shaft speed is set at 50.0 centimeters per minute per full stroke length. Any release paper is removed from the absorbent article prior to placement in the apparatus, and talc powder is applied to exposed positioning adhesive to provide a tackless surface. The article is placed, with cover facing down and the barrier facing up, in the holder 54, and the shaft 55 is actuated. The peak loads are measured for 5 cycles. Values are reported as peak Load 1, peak load 5, and % drop between load 1 and load 5.

**[0027]** The Bunching Resistance of the present absorbent article is very high, higher than that of known absorbent articles of similar thickness. The low level of bunching experienced with these products provides a more comfortable body facing surface against the skin and avoids the formation of channels that encourage the fluid to flow laterally out of the absorbent article.

**[0028]** The following non-limiting examples further illustrate the invention.

#### Examples 1-15 and A-II

**[0029]** A series of pantliners having thicknesses in the range of 0.06 to 0.2 inches were subjected to the Curved Longitudinal Bending Test using the apparatus shown in Figure 2. Examples A-II were commercially available pantliners, while Examples 1-15 were pantliners of the invention.

**[0030]** Specifically, the pantliners of Examples 1-15 comprised a liquid permeable cover, an absorbent core comprising two absorbent layers, and a barrier. The absorbent layer adjacent the liquid permeable cover was made of about 50 to 65% pulp, the remainder being a combination of polyethylene/polypropylene bicomponent fibers and polyethylene/polyester bicomponent fibers. The absorbent layer adjacent the barrier was made of less than about 50% pulp, the remainder being a combination of polyethylene/polypropylene bicomponent fibers and polyethylene/polyester bicomponent fibers. It should be noted that the pantliners of Examples 6-10 were handmade samples.

**[0031]** The results are given in the Tables.

Table 1

Invention	
Example	Bend Resistance [g]
1	298.1
2	293

# EP 1 066 810 A2

Table 1 (continued)

Invention	
Example	Bend Resistance [g]
3	296.1
4	246.4
5	271
Mean:	280.92
6	186
7	165.1
8	175.6
9	183.3
10	166.8
Mean:	175.36
11	259.3
12	238.4
13	243.4
14	261.5
15	231
Mean:	246.72

Table 2

ALWAYS ALLDAYS*	
Example	Bend Resistance [g]
A	198.4
B	196.3
C	173.9
D	170.5
E	201.4
Mean:	188.1

\* Commercially available from  
Procter & Gamble Company.

Table 3

ALLDAYS Light*	
Example	Bend Resistance [g]
F	197.2
G	192.1
H	190.9
I	204
J	192
Mean:	195.24

\* Commercially available from  
Procter & Gamble Company.

Table 4

KOTEX Lightdays**	
Example	Bend Resistance [g]
K	102.0
L	104.7
M	98.9
N	101.9
O	82.1
P	75.4
Q	85.1
R	94.3
S	88.1
T	101.5
Mean:	93.4

\*\* Commercially available from  
Kimberly Clark Corp.

Table 5

CAREFREE To Go***	
Example	Bend Resistance [g]
U	55.1
V	49.3
W	39.5
X	45.7
Y	39.2
Z	49.3
AA	46.3
BB	53.1
CC	36.8
DD	41.4
EE	43.2
FF	44.3
GG	48.9
HH	38.8
II	42.1
Mean:	44.9

\*\*\* Commercially available from  
Personal Products Worldwide, a  
division of McNeil-PPC, Inc.

### Examples 16-35

[0032] Ten, two layer absorbent cores of the same type used in the pantliners of Examples 1-15 were tested for Gurley Stiffness as follows. In each case, the two absorbent layers were separated from each other, and the Gurley Stiffness of each layer was measured according to by TAPPI T543 om-94. The results are shown in Tables 6 and 7. Examples 16-25 were the absorbent layers proximal the covers of the pantliners (5g weight in the 2 inch position, factor 11.1). Examples 26-35 were the absorbent layers proximal the barriers of the pantliners (25g weight in the 2 inch position, factor 55.6).

Table 6

Gurley Stiffness	
Example	Milligrams
16	36.075
17	24.975
18	31.635
19	30.525
20	28.86
21	35.52
22	40.515

EP 1 066 810 A2

Table 6 (continued)

Gurley Stiffness	
Example	Milligrams
23	25.53
24	27.195
25	30.525
Average	31.14

Table 7

Gurley Stiffness	
Example	Milligrams
26	155.68
27	183.48
28	155.68
29	169.58
30	144.56
31	177.92
32	183.48
33	150.12
34	177.92
35	166.8
Average	166.52

**Example 37**

[0033] Several commercially available pantliners and two having the same construction as the pantliners of Examples 1-15 were tested for comfort with groups of consumers. The consumers were asked to use the pantliners and rate them on a scale of 1 to 10 for comfort to wear. The results are given in Table 8.

Table 8

Comfort		
Product	Average Rating for Comfort to Wear (0-10)	Number of Women
Kao*	7.5	104
KOTEX Lightdays**	7.6	140
ALLDAYS Light***	8	153
Invention	8.5	140
ALWAYS Alldays***	7.7	140
Invention	8	140

\* Commercially available from Kao Corp.

\*\* Commercially available from Kimberly Clark Corp.


\*\*\* Commercially available from Procter & Gamble Company.




Claims

1. An absorbent article comprising in sequence a liquid permeable cover, an absorbent core, and a barrier, wherein the absorbent article has a caliper of less than about 0.2 inches, a length of less than about 8 inches, a width of less than about 4 inches, and exhibits a Bunching Resistance of about 205 g to about 450 g.
2. The absorbent article of claim 1, wherein the Bunching Resistance is at about 250 g to about 360 g.
3. The absorbent article of claim 1, wherein the absorbent core comprises at least two absorbent layers having different Gurley Stiffnesses.
4. The absorbent article of claim 3, wherein the absorbent core comprises a first absorbent layer proximal the liquid permeable cover having a Gurley Stiffness of less than about 50 milligrams and a second absorbent layer proximal the barrier having a Gurley Stiffness greater than about 120 milligrams.
5. The absorbent article of claim 3, wherein the absorbent core comprises three absorbent layers in sequence, wherein the first and third layers sandwich the second layer and have the substantially the same Gurley Stiffness, while the second layer has a different Gurley Stiffness.
6. The absorbent article of claim 1, wherein the absorbent core comprises one absorbent layer having a Gurley Stiffness that varies along its length or width.
7. The absorbent article of claim 1, wherein the absorbent core comprises superabsorbent polymer.
8. An absorbent article comprising in sequence a liquid permeable cover, an absorbent core comprising at least two absorbent layers having different Gurley Stiffnesses, and a barrier.
9. The absorbent article of claim 8 having a caliper of less than about 0.2 inches, a length of less than about 8 inches, and a width of less than about 4 inches.
10. The absorbent article of claim 8, wherein the absorbent core comprises a first absorbent layer proximal the liquid permeable cover having a Gurley Stiffness less than 50 milligrams and a second absorbent layer proximal the barrier having a Gurley Stiffness greater than 120 milligrams.
11. The absorbent article of claim 9, wherein the absorbent core comprises superabsorbent polymer.

**FIG. 1**



**FIG. 2**





(12) **EUROPEAN PATENT APPLICATION**

(88) Date of publication A3:  
**08.08.2001 Bulletin 2001/32**

(51) Int Cl.7: **A61F 13/15, A61F 13/53**

(43) Date of publication A2:  
**10.01.2001 Bulletin 2001/02**

(21) Application number: **00114416.1**

(22) Date of filing: **05.07.2000**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU**  
**MC NL PT SE**  
Designated Extension States:  
**AL LT LV MK RO SI**

• **Corley, Michelle Renee**  
**West Windsor, NJ 08550 (US)**  
• **Haarer Jutta S.**  
**Lawrenceville NJ 08648 (US)**

(30) Priority: **07.07.1999 US 348956**

(71) Applicant: **McNeil-PPC, Inc.**  
**Skillman, NJ 08558-9418 (US)**

(74) Representative:  
**Groening, Hans Wilhelm, Dipl.-Ing.**  
**BOEHMERT & BOEHMERT**  
**Franz-Joseph-Strasse 38**  
**80801 München (DE)**


(72) Inventors:  
• **Bissah, Kofi Ayensu**  
**Somerset, NJ 08873 (US)**

(54) **Bunching resistant absorbent article**

(57) An absorbent article, such as a pantliner, is provided having excellent resistance to bunching. The absorbent article exhibits a Bunching Resistance in the

range of about 205g to 450 g and may be formed with an absorbent core comprising at least two absorbent layers having different Gurley Stiffnesses.

**FIG. 1**





European Patent  
Office

## EUROPEAN SEARCH REPORT

Application Number  
EP 00 11 4416

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	EP 0 442 223 A (CHICOPEE) 21 August 1991 (1991-08-21) * column 5, line 8 - column 6, line 54 * * column 10, line 33-45 * * column 15, line 32-56; figures 2,5-8 *	1-4,6-11	A61F13/15 A61F13/53
X	GB 2 170 108 A (MOELNLYCKE AB) 30 July 1986 (1986-07-30) * claim 1; figures 1-3 *	1-4,7-11	
X	US 5 423 787 A (KJELLBERG MONICA M L) 13 June 1995 (1995-06-13) * column 4, line 9-32; figures 1,2 *	1-4,7-11	
X	EP 0 172 035 A (PERSONAL PRODUCTS CO) 19 February 1986 (1986-02-19) * page 9, line 19 - page 10, line 4; figures 5,6,10 *	1,5	
A	WO 93 21879 A (PROCTER & GAMBLE) 11 November 1993 (1993-11-11) * page 10, line 24 - page 11, line 17 * * page 22, line 7-23; claim 6; figures 2,6 *	5	TECHNICAL FIELDS SEARCHED (Int.Cl.7) A61F
X	GB 2 319 187 A (MOELNLYCKE AB) 20 May 1998 (1998-05-20) * page 6, line 11 - page 7, line 24 * * page 17, line 24 - page 18, line 24; figures 1,5,6 *	1,2,6,7	
X	US 5 591 150 A (BITTAR SANDRA R ET AL) 7 January 1997 (1997-01-07) * column 3, line 6-24 * * column 21, line 64 - column 22, line 59; figures 15A-22 *	1,6	
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 15 June 2001	Examiner Seabra, L
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

EPO FORM 1503 03 82 (p04c01)

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 11 4416

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.  
The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

15-06-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0442223 A	21-08-1991	AT 118338 T	15-03-1995
		BR 9100116 A	22-10-1991
		DE 69017001 D	23-03-1995
		DE 69017001 T	12-10-1995
		ES 2076341 T	01-11-1995
		IE 910092 A	17-07-1991
		ZA 9100244 A	30-09-1992
GB 2170108 A	30-07-1986	SE 453556 B	15-02-1988
		DE 3600420 A	31-07-1986
		DK 41186 A	31-07-1986
		FR 2581844 A	21-11-1986
		JP 61179309 A	12-08-1986
		NL 8600024 A	18-08-1986
		NO 855332 A	31-07-1986
		SE 8500418 A	31-07-1986
US 5423787 A	13-06-1995	SE 501146 C	28-11-1994
		AT 118337 T	15-03-1995
		AU 648549 B	28-04-1994
		AU 7564991 A	21-10-1991
		CA 2077915 A	27-09-1991
		DE 69107451 D	23-03-1995
		DE 69107451 T	14-06-1995
		DK 523107 T	01-05-1995
		EP 0523107 A	20-01-1993
		ES 2067929 T	01-04-1995
		FI 924299 A	25-09-1992
		GR 3015281 T	30-06-1995
		HU 64827 A	28-03-1994
		JP 5505122 T	05-08-1993
		NO 180515 B	27-01-1997
		SE 9001092 A	27-09-1991
		WO 9114415 A	03-10-1991
EP 0172035 A	19-02-1986	US 4559050 A	17-12-1985
		US 4605402 A	12-08-1986
		AT 68092 T	15-10-1991
		AU 580796 B	02-02-1989
		AU 4627985 A	20-02-1986
		BR 8503822 A	20-05-1986
		CA 1252953 A	25-04-1989
		DE 3584335 A	14-11-1991
		ES 546180 D	01-10-1986
		ES 8700340 A	01-01-1987
		GR 851976 A	16-12-1985

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 11 4416

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.  
The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

15-06-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0172035 A		HK 107691 A	03-01-1992
		IN 165380 A	07-10-1989
		JP 1857476 C	27-07-1994
		JP 5068261 B	28-09-1993
		JP 61085943 A	01-05-1986
		NZ 212996 A	30-03-1988
		PH 21004 A	23-06-1987
		PT 80968 A, B	01-09-1985
		SG 95591 G	13-12-1991
		ZA 8506250 A	25-03-1987
		AU 580325 B	12-01-1989
		AU 4627785 A	20-02-1986
		BR 8503820 A	20-05-1986
		CA 1251901 A	04-04-1989
		ES 546182 D	01-10-1986
		ES 8700342 A	01-01-1987
		GR 851979 A	16-12-1985
		IN 164134 A	21-01-1989
		JP 1857478 C	27-07-1994
		JP 5069545 B	01-10-1993
		JP 61085942 A	01-05-1986
		MX 169989 B	03-08-1993
		NZ 213029 A	30-06-1987
		PH 20869 A	25-05-1987
		PT 80970 A, B	01-09-1985
		ZA 8506252 A	25-03-1987
WO 9321879 A	11-11-1993	AT 143247 T	15-10-1996
		AT 148831 T	15-02-1997
		AT 174208 T	15-12-1998
		AT 155032 T	15-07-1997
		AT 142468 T	15-09-1996
		AT 149823 T	15-03-1997
		AT 171057 T	15-10-1998
		AU 2383092 A	23-02-1993
		AU 2383192 A	23-02-1993
		AU 2399392 A	23-02-1993
		AU 662350 B	31-08-1995
		AU 2402592 A	23-02-1993
		AU 662757 B	14-09-1995
		AU 2420492 A	23-02-1993
		AU 2421392 A	23-02-1993
		AU 2507595 A	14-09-1995
		AU 2507695 A	14-09-1995
		AU 4021895 A	29-02-1996
		AU 4021995 A	29-02-1996

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 11 4416

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.  
The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

15-06-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9321879 A		AU 678554 B	05-06-1997
		AU 4291193 A	29-11-1993
		AU 5844198 A	04-06-1998
		AU 5951498 A	01-10-1998
		AU 5954298 A	01-10-1998
		AU 8189298 A	15-10-1998
		AU 8307898 A	24-12-1998
		BR 9205320 A	05-04-1994
		BR 9205329 A	05-10-1993
		BR 9205330 A	16-11-1993
		BR 9306304 A	30-06-1998
		CA 2092197 A	24-01-1993
		CA 2092198 A,C	24-01-1993
		CA 2092199 A	24-01-1993
		CA 2092202 A,C	24-01-1993
		CA 2092203 A	24-01-1993
		CA 2092204 A,C	24-01-1993
		CA 2118215 A,C	11-11-1993
		CA 2195690 A	24-01-1993
		CA 2226415 A	11-11-1993
		CA 2243039 A	24-01-1993
		CA 2243049 A	24-01-1993
		CA 2243053 A	24-01-1993
		CA 2243056 A	24-01-1993
		CA 2243106 A	24-01-1993
		CA 2243108 A	24-01-1993
		CA 2243115 A	24-01-1993
		CA 2243117 A	24-01-1993
		CA 2243119 A	24-01-1993
		CZ 9300711 A	17-11-1993
		CZ 9300712 A	17-11-1993
GB 2319187 A	20-05-1998	SE 514462 C	26-02-2001
		AU 726970 B	30-11-2000
		AU 5074598 A	10-06-1998
		EP 0944373 A	29-09-1999
		PL 333360 A	06-12-1999
		SE 9604222 A	22-06-1998
		WO 9822058 A	28-05-1998
US 5591150 A	07-01-1997	SK 62199 A	14-02-2000
		US 5334176 A	02-08-1994
		US 5824004 A	20-10-1998
		US 5356405 A	18-10-1994
		AU 701627 B	04-02-1999
		AU 2360895 A	05-12-1995

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82



**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 11 4416

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

15-06-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5591150 A		AU 9712098 A	04-03-1999
		EP 0749297 A	27-12-1996
		JP 10500047 T	06-01-1998
		KR 231313 B	15-11-1999
		WO 9531165 A	23-11-1995
		ZA 9503794 A	16-04-1996
		AT 184475 T	15-10-1999
		AT 142467 T	15-09-1996
		AT 143247 T	15-10-1996
		AT 148831 T	15-02-1997
		AT 174208 T	15-12-1998
		AT 155032 T	15-07-1997
		AT 142468 T	15-09-1996
		AT 149823 T	15-03-1997
		AU 669118 B	30-05-1996
		AU 2318392 A	23-02-1993
		AU 663104 B	28-09-1995
		AU 2374292 A	23-02-1993
		AU 2383092 A	23-02-1993
		AU 2383192 A	23-02-1993
		AU 2399392 A	23-02-1993
		AU 662350 B	31-08-1995
		AU 2402592 A	23-02-1993
		AU 662757 B	14-09-1995
		AU 2420492 A	23-02-1993
		AU 2421392 A	23-02-1993
		AU 2507595 A	14-09-1995
		AU 2507695 A	14-09-1995
		AU 4021895 A	29-02-1996
		AU 4021995 A	29-02-1996
		AU 5844198 A	04-06-1998
		AU 5951498 A	01-10-1998
		AU 5954298 A	01-10-1998
		AU 8189298 A	15-10-1998
		AU 8307898 A	24-12-1998
		BR 9205320 A	05-04-1994
		BR 9205329 A	05-10-1993
		BR 9205330 A	16-11-1993
		BR 9205346 A	16-11-1993
		BR 9206307 A	02-08-1994
		CA 2092196 A, C	24-01-1993
		CA 2092197 A	24-01-1993
		CA 2092198 A, C	24-01-1993
		CA 2092199 A	24-01-1993
		CA 2092202 A, C	24-01-1993

EPO FORM P4459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

